SEFAR® METALEN





Metal coated PET Monofilament

Metall beschichtetes PET Monofilament

SEFAR

1. Product reference	2. Mesh opening [µm]	3. Open area [%]	4. Mesh count, warp [n/cm]	5. Mesh count, weft [n/cm]	6. Mesh count, warp [n/in]	7. Mesh count, weft [n/in]	8. Wire diameter, warp [µm]	9. Wire diameter, weft [µm]	10. Weight [g/m²]	11. Weight [oz/yd²]	12. Thickness [µm]	13. Width on stock [cm]	14. Width on request [cm]
SEFAR METALEN													
07-51/33 AL	51	33	113.0	113.0	287	287	38	38	30	0.9	60	-	102
07-53/29 NI	53	29	100.0	100.0	254	254	45	45	70	2.1	75	-	104
07-87/28 NI	87	28	61.0	61.0	155	155	74	74	95	2.8	118	-	104
07-105/52 AL	105	52	69.0	69.0	175	175	42	42	25	0.7	61	-	102
07-115/36 AL	115	36	54.0	54.0	137	137	70	70	55	1.6	105	102	-
07-120/41 AL	120	41	54.0	54.0	137	137	70	70	25	0.7	64	102	-
07-285/55 AL	285	55	26.0	26.0	66	66	103	103	60	1.8	168	102	-
07-395/36 NI	395	36	15.0	15.0	38	38	250	250	223	6.6	425	-	135

Sefar Headquarter
Sefar AG
Filtration Division
P.O. Box
CH-9410 Heiden
Switzerland
Phone +41 71 898 57 00
Fax +41 71 898 57 21
E-mail filtration@sefar.com

Sefar Filtration Inc.
Buffalo
111 Calumet Street
Depew, New York 14043
USA
Toll Free +1 877 481 3626
Phone +1 716 683 4050
Fax +1 716 683 4053
E-mail filtration@sefar.us

In accordance with Sefar's policy of continuous product improvement, specifications and other information in this publication are subject to change without notice.
The user is responsible for determining fitness, merchantability and suitability of purpose before use.

Quality System ISO 9001

Im Einklang mit der Sefar-Geschäftspolitik, die eine dauernde Kontrolle und Verbesserung unserer Produkte definiert, behalten wir uns die Änderung der technischen Daten jederzeit vor.
Der Endverbraucher ist verpflichtet, die verwendeten Produkte auf deren Eignung zum Verwendungszweck vor dem Einsatz zu prüfen.

Sefar Singapore Pte Ltd.
371 Beach Road
KeyPoint, #21-01/02/03
Singapore 199597
Phone +65 6 299 90 92
Fax +65 6 299 63 59
E-mail info.sg@sefar.com

www.sefar.com

200/ 03.2008